

報告編號: HV-20-05701

數:1 OF

報告日期: 2020年 10月 05日

星彦塑膠股份有限公司

彰化縣秀水鄉鶴鳴村馬鳴路 92 號

稱: KT-001.KT-002 BLACK-7210NS*45P 產 品

產 品 型 號: PVC PELLET

色: BLACK 產 品 顏

製 商: 星彥塑膠股份有限公司 浩

商: 星彥塑膠股份有限公司 送 驗

期: 2020年 09月 22日 收 件

期: 2020年 09月 22日~2020年 10月 05日 試 驗 日

註: 1.以上資料由顧客提供(收件及試驗日期除外) 備

> 2.除非另有說明,此報告結果僅對測試之樣品負責 未經本公司事先書面同意,此報告不可部分複製

3.下述報告內容標示#處由顧客提供

4.本樣品由 SGS 材料暨工程實驗室-高雄(申請書號碼: KV-20-06972,

收件日期:2020年08月27日)轉送至本實驗室執行本報告所示之試驗項目。

本實驗室依據顧客所提供之試驗需求與樣品進行試驗,結果說明如下:

試驗需求:燃燒試驗

試驗方法:請參見附頁

試驗結果:請參見附頁

註:本試驗報告之試驗地點同實驗室地址。

本報告若有提供規範值,該規範值僅供參考,合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized attention, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TWC 7 9 0 8 7 5 6



報告編號: HV-20-05701

數:2

OF

報告日期: 2020年 10月 05日

燃燒試驗

試驗設備:

	~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~	型號		
150 mm 數位式卡尺	MITUTOYO	500-196-30		
Horizon Vertical Flame	ATLAS	HVUL2		
Chamber	ALAS	HVUL2		

試驗方法:

參考 UL 94 (2013)

Test for Flammability of Plastic Materials for Parts in

Devices and Appliances

試驗條件:

調節狀態1:

溫度 23±2℃,相對濕度 50±10%,至少 48 小時

調節狀態2:

溫度 70±2℃中 168±2 小時,室溫乾燥器中至少 4 小時

---- 2 -----

本報告若有提供規範值,該規範值僅供參考,合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aspx">http://www.sgs.com/en/Terms-and-Conditions.aspx</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx">http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx</a>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



# 試驗報告

報告編號: HV-20-05701

數:3

OF

報告日期: 2020年 10月 05日

## 試驗結果:

調節狀態 1(溫度 23±2℃, 相對濕度 50±10%, 至少 48 小時)

試驗項目	試片				#要求值			
	1	2	3	4	5	V-0	V-1	V-2
試片厚度(mm)	3.10	3.11	3.08	3.09	3.10	-	_	-
每一試片餘焰時間 t1(秒)	1.4	0	0	0.7	0	<b>≦</b> 10	≦30	<b>≦</b> 30
每一試片餘焰時間 t2(秒)	2.4	4.7	7.4	3.3	6.1	<b>≦</b> 10	≦30	≦30
每5片一組的總餘焰時間(秒)	26.0				<b>≤</b> 50	<b>≤</b> 250	<b>≤</b> 250	
(5 片各個 t1+t2 的總和)					≥30	≥230	≥230	
每一試片第二次點火燃燒後的餘	2.4	4.7	7.4	3.3	6.1	≦30	<b>≦</b> 60	≦60
焰加餘燼的時間 t2+t3(秒)								
任一試片的餘焰或餘燼燒至夾具	否	否	否	否	否	否	否	否
棉花被燃燒顆粒或熔滴物點燃	否	否	否	否	否	否	否	是

### 調節狀態 2(溫度 70±2℃中 168±2 小時,室溫乾燥器中至少 4 小時)

試驗項目	試片				#要求值			
	1	2	3	4	5	V-0	V-1	V-2
試片厚度(mm)	3.09	3.11	3.11	3.09	3.09	-	-	-
每一試片餘焰時間 t1(秒)	2.0	0.7	2.5	1.4	1.1	<b>≦</b> 10	<b>≦</b> 30	<b>≦</b> 30
每一試片餘焰時間 t2(秒)	4.0	2.6	4.5	0	2.9	≦10	≦30	≦30
每5片一組的總餘焰時間(秒)	21.7				<b>≤</b> 50	≦250	≦250	
(5 片各個 t1+t2 的總和)					≥30			
每一試片第二次點火燃燒後的餘	4.0	2.6 4.5	4.5 0	0	2.0	≤30	< 60	<60
焰加餘燼的時間 t2+t3(秒)				2.9	$  \ge 30$	$\leq 60$	$\leq 60$	
任一試片的餘焰或餘燼燒至夾具	否	否	否	否	否	否	否	否
棉花被燃燒顆粒或熔滴物點燃	否	否	否	否	否	否	否	是

---- 3 -----

### 本報告若有提供規範值,該規範值僅供參考,合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aspx">http://www.sgs.com/en/Terms-and-Conditions.aspx</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx">http://www.sgs.com/en/Terms-and-Conditions.aspx</a> attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.




# 試驗報告

報告編號: HV-20-05701

頁 數:4 OF

報告日期: 2020年 10月 05日

樣品照片:



---- o O o -----

## 本報告若有提供規範值,該規範值僅供參考,合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aspx">http://www.sgs.com/en/Terms-and-Conditions.aspx</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx">http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx</a>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's spice responsibility is to its Client and this document does not exonerate parties to a transaction form exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TWC 7 9 0 8 75 3

TWC 7 9 0 8 75 3